



Product Data Sheet

G 'Gas-shielded metal-arc welding'

Weld G3Si1

Prepared by Mirjam Hamsten	Qualified by Tero Tolonen	Approved by Per-Erik Andersson	Reg no EN006756	Cancelling EN006745	Reg date 2015-06-29	Page 1 (2)
-------------------------------	------------------------------	-----------------------------------	--------------------	------------------------	------------------------	---------------

REASON FOR ISSUE

DB approval

GENERAL

A copper coated, G3Si1 solid wire for GMAW of all general structural and engineering unalloyed and low-alloyed carbon-manganese steels. The electrode may be welded with either a gas mixture or with pure CO₂ as the shielding gas.

Shielding Gas: M21, C1 (EN ISO 14175)

Alloy Type: Carbon-manganese steel (Mn/Si-alloyed)

CLASSIFICATIONS Weld Metal

EN ISO 14341-A G 38 2 C1 3Si1
EN ISO 14341-A G 42 3 M21 3Si1

CLASSIFICATIONS Wire Electrode

EN ISO 14341-A G 3Si1
SFA/AWS A5.18 ER70S-6

APPROVALS

CE EN 13479
DB 42.039.39
VdTÜV 13038

CHEMICAL COMPOSITION

Wire/Strip (%)

	Min	Max
C	0.06	0.14
Si	0.80	1.00
Mn	1.40	1.60
P		0.025
S		0.025

MECHANICAL PROPERTIES OF WELD METAL

All Weld Metal

Properties	EN CO ₂ (C1)		EN 80Ar/20CO ₂ (M21)	
	Min	Max	Min	Max
ReL (MPa)	380		420	
Rm (MPa)	510	600	510	640
A4-A5 (%)	22		22	
Charpy V at -20°C (J)	47			
Charpy V at -30°C (J)			47	



Product Data Sheet

G 'Gas-shielded metal-arc welding'

Weld G3Si1

Prepared by Mirjam Hamsten	Qualified by Tero Tolonen	Approved by Per-Erik Andersson	Reg no EN006756	Cancelling EN006745	Reg date 2015-06-29	Page 2 (2)
-------------------------------	------------------------------	-----------------------------------	--------------------	------------------------	------------------------	---------------

ECONOMICS & CURRENT DATA

Dimension (mm) Ø	Current (A)		W Nom	η Nom	H		Feed			U	
	Min	Max			Min	Max	Min	Max	Min	Max	
0.8	60	180	14	95	0,8	2,6	3,2	11	18	22	
1.0	80	250	16	96	1	4,8	2,7	13	18	30	
1.2	120	330	18	97	1,3	6,9	2,3	13	18	34	

W = Gas consumption (l / min)

η = Recovery, g weld metal / 100g wire (%)

H = Deposit rate (kg weld metal / hour arc time)

Feed = Feeding rate (m/min)

U = Arc voltage (V)